

Inlays

Preparation

Shoulder margin
Rounded internal line angles
1.0 mm isthmus width
1.0 mm to 1.5 mm wide gingival floor
1.0 mm depth at isthmus

Material Options:
IPS e.max Lithium Disilicate

Cementation (must be adhesively cemented)

Recommended
Multilink Automix
Variolink II
Variolink Veneer

Other:
Adhesive Resin Cements

Contraindication:
Temporary Cements
Self-Adhesive Cements
Glass Ionomer Cements
Resin Modified Glass Ionomer

Onlays

Preparation

1.0 mm to 1.5 mm wide gingival floor
Shoulder margin
Occlusal reduction of 1.5 mm

Material Options:
IPS e.max Lithium Disilicate

Cementation (must be adhesively cemented)

Recommended
Multilink Automix
Variolink II
Variolink Veneer

Other:
Adhesive Resin Cements

Contraindication:
Temporary Cements
Self-Adhesive Cements
Glass Ionomer Cements
Resin Modified Glass Ionomer

Anterior Crowns

Preparation

Shoulder margin
1.0 mm reduction at gingival margin
Shoulder margin
1.2 mm to 1.5 mm facial reduction
1.2 mm lingual contact clearance
1.5 mm incisal reduction
Rounded internal line angles
Football-shaped finishing bur for lingual reduction

Material Options: IPS e.max Lithium Disilicate, IPS e.max ZirCAD

Cementation

Retentive Preparation	Non-Retentive Preparation
<p>Recommended Multilink Automix Variolink II SpeedCEM</p> <p>Other: Adhesive Resin Cements Self-Adhesive Cements Glass Ionomer Cements Resin Modified Glass Ionomer</p> <p>Contraindication: Temporary Cements</p>	<p>Recommended Multilink Automix Variolink II</p> <p>Other: Adhesive Resin Cements</p> <p>Contraindication: Self-Adhesive Cements Glass Ionomer Cements Resin Modified Glass Ionomer Temporary Cements</p>

Posterior Crown

Preparation

Rounded internal line angles
1.5 mm to occlusal reduction
1.5 mm axial reduction
1.0 mm reduction at the gingival margin
A flat-ended tapered diamond is utilized to establish a shoulder margin

Material Options: IPS e.max Lithium Disilicate, IPS e.max ZirCAD

Cementation

Retentive Preparation	Non-Retentive Preparation
<p>Recommended Multilink Automix Variolink II SpeedCEM</p> <p>Other: Adhesive Resin Cements Self-Adhesive Cements Glass Ionomer Cements Resin Modified Glass Ionomer</p> <p>Contraindication: Temporary Cements</p>	<p>Recommended Multilink Automix Variolink II</p> <p>Other: Adhesive Resin Cements</p> <p>Contraindication: Self-Adhesive Cements Glass Ionomer Cements Resin Modified Glass Ionomer Temporary Cements</p>

Veneers

Preparation

0.7 mm incisal reduction
Depth cuts of 0.6 mm*

Material Options:
IPS e.max Lithium Disilicate

Cementation (must be adhesively cemented)

Recommended
Variolink Veneer
Variolink II

Other:
Adhesive Resin Cements

Contraindication:
Temporary Cements
Self-Adhesive Cements
Glass Ionomer Cements
Resin Modified Glass Ionomer

Posterior Bridge

Preparation

1.5 mm to occlusal reduction
Rounded internal line angles
1.5 mm reduction at the gingival margin
Rounded internal line angles
Shoulder margin
1.0 mm reduction at the gingival margin
1.5 mm to 2.0 mm occlusal reduction
1.5 mm axial reduction

Material Options: IPS e.max CAD-on, IPS e.max ZirCAD

Cementation

Retentive Preparation	Non-Retentive Preparation
<p>Recommended Multilink Automix Variolink II SpeedCEM</p> <p>Other: Adhesive Resin Cements Self-Adhesive Cements Glass Ionomer Cements Resin Modified Glass Ionomer</p> <p>Contraindication: Temporary Cements</p>	<p>Recommended Multilink Automix Variolink II</p> <p>Other: Adhesive Resin Cements</p> <p>Contraindication: Self-Adhesive Cements Glass Ionomer Cements Resin Modified Glass Ionomer Temporary Cements</p>

Anterior Bridge

Preparation

Rounded internal line angles
Shoulder margin
1.0 mm reduction at the gingival margin
1.5 mm axial reduction
1.5 mm incisal reduction

Material Options: IPS e.max Lithium Disilicate, IPS e.max CAD-on, IPS e.max ZirCAD

Cementation

Retentive Preparation	Non-Retentive Preparation
<p>Recommended Multilink Automix Variolink II SpeedCEM</p> <p>Other: Adhesive Resin Cements Self-Adhesive Cements Glass Ionomer Cements Resin Modified Glass Ionomer</p> <p>Contraindication: Temporary Cements</p>	<p>Recommended Multilink Automix Variolink II</p> <p>Other: Adhesive Resin Cements</p> <p>Contraindication: Self-Adhesive Cements Glass Ionomer Cements Resin Modified Glass Ionomer Temporary Cements</p>

Clinical Case Guide

Cement Procedures							
	STEP 1		STEP 2		STEP 3	STEP 4	STEP 5
	IPS e.max Restoration Conditioning		Tooth Conditioning		Cement	Clean Up	Final Cure
	Etching Restoration	Priming Restoration	Etching Tooth	Priming Tooth			View
	Apply IPS Ceramic Etching Gel (5% HF Acid) for 20 seconds to bonding surface of the restoration. Rinse thoroughly and air dry.	Apply Monobond Plus Universal Primer to the bonding surface of the restoration. Allow to react for 60 sec. Completely air dry.	Apply Total Etch 37% Phosphoric Acid etching gel. (15 secs on dentin, 30 secs on enamel) Rinse and dry leaving prepared surface moist.	Apply bonding agent to moist preparation	Mix and dispense cement into restoration	After seating, light cure each quarter surface for 1-2 sec. The cement will achieve a gel-like consistency for easy clean-up.	Optional: Utilize Liquid Strip (glycerin gel) along the margins to eliminate oxygen-inhibition layer. Light cure each side on high power for 20 sec.
Variolink® III Variolink® Veneer							
			<i>Scrub Excite F on preparation for 10 seconds. Thin with air and light cure.</i>				
Multilink® Automix			Not Required				
				<i>Scrub self-etching Primer 1:1 mixture into the prepared surface. (30 sec. on enamel and 15 sec. on dentin) Air dry</i>			
SpeedCEM®			Not Required				

Clinical Recommendation

Efficient rotary cutting instruments for high-strength ceramics

- When removing a high-strength ceramic restoration, proper bur selection improves the efficiency of the procedure, reducing the time needed for completion.
- The use of an electric handpiece is preferable due to its superior cutting efficiency and reduced heat generation.
- Regardless of the cutting instrument or the handpiece used, copious water irrigation is paramount when cutting through ceramic materials. Water acts as a lubricant, improves cutting efficiency and prevents heat rise in the restoration and the tooth underneath.

MANUFACTURER	BUR	GRIT SIZE	FOOTBALL SHAPE FOR OCCLUSAL REDUCTION	ROUND SHAPE FOR ENDODONTIC ACCESS	CYLINDER SHAPE FOR CROWN REMOVAL
Komet	ZR Diamond	Coarse 126µm	Excellent (ZR6379.314.023)	Excellent (ZR6801.314.014)	Excellent (ZR6856.314.025)
Brasseler USA	DuraCut	Coarse 151µm	Excellent (6368DC.31.023)	Very good (6801DC.31.023)	Very good (6856DC.31.018)
Dentalree	Crosstech	Coarse 150µm	Excellent (368.031.023)	Very good (801.31.018)	Good (856.31.018)
SS White	Great White Z		Excellent (GWZ 379-023)	Very good (GWZ 801-018)	Good (GWZ 856-018)

Tested at applied testing facility, Ivoclar Vivadent Amherst

100% CUSTOMER SATISFACTION
GUARANTEED!

ivoclarvivadent.com

©2011 Ivoclar Vivadent, Inc.
IPS e.max, Variolink, Multilink, SpeedCEM are registered trademarks of Ivoclar Vivadent.
Komet, ZR Diamond, Brassler USA, DuraCut, Dentalrec, Crosstech, SS White, and Great White Z are not registered trademarks of Ivoclar Vivadent.
2/2011 Rev. 1

United States
175 Pineview Drive
Amherst, NY 14228
716.691.0010
800.533.6825
Fax: 716.691.2285
mail@ivoclarvivadent.com

Canada
2785 Skymark Avenue, Unit 1
Mississauga, Ontario L4W 4Y3
905.238.5700
800.263.8182
Fax: 905.238.5711
mail@ivoclarvivadent.com

ivoclar vivadent
passion vision innovation